

WIRAND® FIBRE FF3**DESCRIPTION:**

WIRAND® FF3 steel wire fibres for concrete reinforcement.

TYPE:

Wirand® FF3

NOMINAL DIMENSIONS:

- Diameter (D) : 0,75 mm
- Length (L) : 50 mm
- Aspect ratio (L/D) : Ratio between length (L) and diameter (D) : $50/0,75 = 67$

WIRE MECHANICAL PROPERTIES:

R_m (Tensile strength of the wire) : > 1100 MPa
 ϵ (Strain at failure) : < 4%

SHAPE:


The ending shapes WIRAND® FF3 fibre are very important to grant adhesion between fibre and concrete.

REFERENCE STANDARDS:

- UNI-EN 10016 "Non-alloy steel rod for drawing and/or cold rolling - Part 1: General requirements".
- UNI-11037 - Fibre di acciaio da impiegare nel confezionamento di conglomerato cementizio rinforzato.
- pr-EN 14889-1 - Fibres for concrete - Part 1: Steel fibres - Definition, specifications and conformity.

PACKAGING:

The WIRAND® FF3 fibre are delivered packed in big bags of 600, 750, 950 kg weight, or in carton boxes of 20 kg.



Maccaferri SA (Pty) Ltd

HEAD OFFICE - DURBAN, SOUTH AFRICA

P O Box 15777, Westmead, 3608 Tel: +27-31-700 8456 Fax: +27-31-700 8469 e-mail: dbnsales@maccaferri.co.za

JOHANNESBURG, SOUTH AFRICA

P O Box 2285, North Riding, 2162 Tel: +27-11-704 0160 Fax: +27-11-704 0159 e-mail: jhbsales@maccaferri.co.za

CAPE TOWN, SOUTH AFRICA

P O Box 22150, Fish Hoek, 7974 Tel: +27-21-702 1416 Fax: +27-21-702 2977 e-mail: cptsales@maccaferri.co.za

MADAGASCAR

BP 168 Antananarivo 101, Madagascar Tel: +261-20-22-231 02 Fax: +261-20-22-553 90 e-mail: maccaferri@moov.mg

www.maccaferri.co.za

